

ANTISILICONAS

Antisilicons Additive



DESCRIPTION ▼

Additive to remove craters produced by the contamination of silicones, oil, grease, etc.
It can be used in paints of different nature, such as synthetic, nitro, acrylic, solvent based 2K PUR.

USE ▼

Add between 1 and maximum 3% of the total amount of paint, homogenise, and carry out the application normally.
It is not recommended to use it as a preventive measure. Exceeding the indicated percentages may result in an increase in the problem.
Do not use in two-coat clearcoats, as this can cause turbidity.

DRY FILM CHARACTERISTICS ▼

Functionality	Crater removal
----------------------	----------------

SAFETY INSTRUCTIONS 

The use of appropriate personal protective equipment is recommended during application, to prevent the irritation of the respiratory tract, skin and eyes. For professional use only.

STORAGE 

Keep in a tightly covered container, in a dry and ventilated place, avoiding direct exposure to sunlight. Temperature above 5°C is recommended, between 15 and 30°C optimal.

VOC 

The VOC content of ANTISILICONAS is a maximum of 827 g/l.

The information contained in this Technical Specification Sheet is based on the knowledge and experience of the BESA technical department, and with it it's intended to advice and inform, being the responsibility of the user to take the necessary measures to guarantee the intended purpose of the product. **FOR PROFESSIONAL USE ONLY.**
