

TECHNICAL DATA SHEET

 BERNARDO ECENARRO, S.A.

 Ugarte Industrialdea, 147

 20720
 Azkoitia (SPAIN)

 Tel.: +34 +34 943 74 28 00

Fax: +34 +34 943 74 06 03

www.besa.es

Page 1 from 1

Edition: 021 2014/01 Cod: 3002500000.00000.021

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Quick drying synthetic primer. Very useful for quick jobs.

F-25 OUICK-DRYING SYNTHETIC PRIMER

Very versatile commonly used in the Machine Tool, Agricultural Machinery, Boilermaking, Forgery Sectors, etc.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,60 - 1,70
Grinding Fineness (µ)	30 - 40
Supply viscosity at 20°C	100 - 120" Ford nº 4
%Solids content (weigth / volume)	74 - 78 % weight; 53% ± 2 volume.
V.O.C. (g/l)	493 (Ready to use)
Type of produtc	Modified Alkyd
Colour	Brown 8012, Greenish grey 1161, White 9110

SURFACE PREPARATION

-Steel and Iron: Previously Deoxidised and Degreased.

-Repainted with top-coats such as: URKI-LAC, URKI-CLOR, URKI-FLEX, BESA-FER, BESA-LUX; MARTELÉ.

APPLICATION INSTRUCTIONS

Dipping: URKISOL-170



FEATURES OF DRY FILM

Theoretical yield (m ² /l)	14 - 16 (35 my)
Gloss 60°-60°	Matt < 2 %
Second layer	6 - 8 h.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended. Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.