

**URKI-FOX 60**  
 METALLIZED PHOSPHATING PRIMER

Edition: 020 2011/11  
 Cod: 3006009006.00000.020

### APPLICATION

Aluminium paint with excellent adhesion on Steel, Galvanized Steel, Aluminium, etc.  
 Good covering and adhesion qualities, resistant to continuous temperatures of up to 200°C, which makes the product suitable for the painting of metallic surfaces in order to achieve a zinc-coating effect as well as to provide a good protection for chimneys, etc.

### PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,90 ± 0,05
Grinding Fineness (μ)	10 - 20
Supply viscosity at 20°C	60 - 65 sec. Ford nº 4
%Solids content (weight / volume)	16 % ± 2 weight; 10% ± 1 volume.
V.O.C. (g/l)	774 (Ready to use) - (2004/42/CE) IIB (C) (780)
Type of product	Modified Vinyl
Colour	Metallized silver 9006

### SURFACE PREPARATION

Degreased and deoxidized, leaving the product as a Top Coat in Metallized Silver 9026.

### APPLICATION INSTRUCTIONS



15-18"  
 FORD nº 4



URKISOL 300  
 40-50%



10-15 my



Touch free 15'  
 Tack free 30'



10'

### FEATURES OF DRY FILM

Theoretical yield (m <sup>2</sup> /l)	9 - 11 (10 my)
Gloss 60°-60°	10 - 15%
Second layer	1 h.

### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended.  
 Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.