

VD 3105
FLASH PRIMER

Edition: 020 2016/06
Cod: 3010500000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Colored air drying flash primer, to be recovered with clear coat VD 7051.
Wet on wet application with clear coat that must be heat cured.
To be applied on glass.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,85 - 0.95
Supply viscosity at 20°C	14 - 18 sec Ford n°4
%Solids content (weigh / volume)	18-22% weight
Colour	Wide color range

SURFACE PREPARATION

The surface should be dry and free from dust, dirt ,grease and oil
It is recommended to flame the substrate.
Substrate temperature should no be higher than 30°C

APPLICATION INSTRUCTIONS

Conventional spray.
Mix well before use.




13-15"
FORD n°4



URKI-SOL 9030
45-50% or 100%



5-7 my



1-3'
20-25°C

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended.
Can life: **6 months** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.