

PD 3505
 CONDUCTIVE PRIMER

Edition: 020 2016/06
 Cod: 3050509005.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Conductive primer 1 C fast air drying .Suitable for PP and different plastic surfaces

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,87 - 0,91
Grinding Fineness (μ)	< 15
Supply viscosity at 20°C	13 - 15" Ford n° 4
%Solids content (weight / volume)	11 % ± 1 weight; 11 % ± 1 volume.
Type of product	Acrylic
Colour	Black 9005

SURFACE PREPARATION

The surface must be free of grease .Perform degreasing and make a careful manipulation of the surface. Degrease with Thinner nº 94.

If the plastic surface is not uniform, it is recommended to heat the workpiece to facilitate mold release any residual emerge to the surface and a good cleaning process

APPLICATION INSTRUCTIONS




13-15"
 FORD nº4



Do not dilute



6-8 my



5'



80°C / 20'

FEATURES OF DRY FILM

Applied film conductivity (Mohmio)	< 0,2
------------------------------------	-------

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended.

Can life: **12 months** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.