

PD 3552
METALLIC PRIMER

Edition: 020 2016/06
Cod: 3055200000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Metallic primer 2K drying oven with good adhesion to PA. It can be used as wet-on-wet primer with monocoat and bicoat systems.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,17 - 1,21
Supply viscosity at 20°C	50 - 70" Ford n° 4
%Solids content (weight / volume)	54 % ± 2 weight; 35 % ± 2 volume.
Type of product	Polyester
Colour	Metallic

SURFACE PREPARATION

The surface must be free of grease .Perform degreasing and make a careful manipulation of the surface. Degrease with Thinner n° 94.

If the plastic surface is not uniform, it is recommended to heat the workpiece to facilitate mold release any residual emerge to the surface and a good cleaning process

APPLICATION INSTRUCTIONS



E-277
100:10 weight



<6h



15-17"
FORD n°4



Urki-Sol 9010
25%



15-20 my



15'

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended.
Can life: **12 months** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.