

F-809

QUICK-DRYING ZINC-PHOSPHATE PRIMER

Edition: 020 2011/11
Cod: 3080900000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Quick-Drying Anti-Rust Synthetic Primer, a high Zinc Phosphate content: resistant up to 300 hours in salt-spray test. Suitable for demanding jobs, excellent hiding power, adhesion in the construction, agricultural machinery, industrial coachwork, boilermaking...

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,30 ± 0,05
Grinding Fineness (μ)	25 - 35
Supply viscosity at 20°C	100 - 130 sec. Ford nº 4
%Solids content (weight / volume)	58 % ± 2 weight; 40 % ± 2 volume.
V.O.C. (g/l)	596 (Ready to use)
Type of product	Modified Alkyd
Colour	Olive Green 6108, Oxide Red 8012

SURFACE PREPARATION

-Steel and Iron: Deoxidized and degreased previously.
-Repaintable with : BESA-VAL, URKI-RAPID, URKI-FLEX, URKI-CLOR, BESA-FER, BESA-LUX, URKI-LAC, URKI-LAC TEXT.

APPLICATION INSTRUCTIONS

Dipping: URKISOL-170



20-25"
FORD nº4



URKISOL 222
5-10%



URKISOL 88
15-20%



30-40 my



Touch free 15'
Tack free 30'



5-10'



URKISOL 88
5%

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	11 - 13 (35 my)
Gloss 60°-60°	Matt < 5 %
Second layer	6 - 8 h. with Synthetics

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended. Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.