

F-450

Q/D SEMIGLOSS SYNTHETIC PAINT

URKI-SYSTEM

CONVERTER: 6037 / CONV F-450

RELATION PASTE / CONV.: 15/85

Edition: 020 2011/11

Cod: 3903700000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Semigloss Synthetic Paint for protection of Metallic Structures, boiler-making, Smithery, Metal Work, forge, etc. Very useful in quick jobs, thanks to its quick drying, excellent adhesion and good general features.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,30 - 1,42
Grinding Fineness (μ)	25 - 35
Supply viscosity at 20°C	100 - 120 sec.Ford nº 4
%Solids content (weight / volume)	66% ± 2 weight; 47 % ± 2 volume.
V.O.C. (g/l)	543 (Ready to use)
Type of product	Modified Alkyd
Colour	URKI-SYSTEM

SURFACE PREPARATION

-Steel and Iron: De-rust and degrease previously.

-Wood: Brush and remove all rust.

If higher resistance to corrosion is needed, we recommend to use F-862, F-25 or F-29 as Synthetics Primer.

APPLICATION INSTRUCTIONS



20-25"
FORD nº 4



URKISOL 222
max.10 %



URKISOL-88 or 170
20-25 %



30-40 my



Touch free 15'
Tack free 1 h.



5-10'



URKISOL-88 or 170
5-10 %

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	13 - 14 (35 my)
Gloss 60°-60°	Half Gloss 55 - 65 %
Second layer	1 h. ó 48 h.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.
Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.