

F-29
 QUICK-DRYING ZINC-PHOSPHATE PRIMER

URKI-SYSTEM
 CONVERTER: 6094 / CONV F-29
 RELATION PASTE / CONV.: 15/85

Edition: 020 2011/11
 Cod: 3909400000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Quick drying Synthetic Primer, with excellent rust protection, quick drying and adhesion. Suitable as a Primer in the Special Boilermaking sector, Agricultural Machinery, Metallic Structures, etc.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,30 - 1,45
Grinding Fineness (µ)	30-40
Supply viscosity at 20°C	75 - 80 KU (Stormer)
%Solids content (weight / volume)	65 - 70 % weight; 50 % ± 2 volume.
V.O.C. (g/l)	547 (Ready to use)
Type of product	Modified Alkyd
Colour	URKI-SYSTEM

SURFACE PREPARATION

- Steel and Iron: Desoxidized and degreased previously.
- Wood: Brush and remove all dust.

Recoatible: BESA-VAL, URKI-RAPID, URKI-FLEX, URKI-CLOR, BESA-POL, BESA-FER, BESA-LUX

APPLICATION INSTRUCTIONS



20-25"
FORD nº 4



URKISOL 222
max. 10 %



URKISOL 170
20-25 %



30-40 my



Touch free 10'
Tack free 30'



5-10'



URKISOL 170
5-10 %

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	13 - 14 (35 my)
Gloss 60°-60°	Matt < 5 %
Second layer	1h. or 24 h. with Synthetics

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended. Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.