

F-862 QUICK DRYING PRIMER FOR STEEL

# **TECHNICAL DATA SHEET**

#### BERNARDO ECENARRO, S.A.

Ugarte Industrialdea, 147 20720 Azkoitia (SPAIN) Tel.: +34 +34 943 74 28 00 Fax: +34 +34 943 74 06 03

www.besa.es

Page 1 from 1

Edition: 021 2014/01 Cod: 3909500000.00000.021

# **URKI-SYSTEM**

CONVERTER: 6095 / CONV F-862 RELATION PASTE / CONV.: 15/85

#### APPLICATION

#### "USE ONLY IN INDUSTRIAL FACILITIES"

Economical primer for the protection of Metallic Structures, Boilermaking, Metallic Carpentry, Blacksmiths, Forge, etc.... It may also be used as a Matt paint for iron and wood, for making marks.

Specially recommended in fast process where a quick drying is recommended. Outstands for its good adhesion and overall properties.

#### PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,35 - 1,50
Grinding Fineness (μ)	40 - 50
Supply viscosity at 20°C	90 - 110 KU (Stormer)
%Solids content (weigth / volume)	71 % $\pm$ 2 weight; 53 % $\pm$ 2 volume.
V.O.C. (g/l)	495 (Ready to use) Airless Application
Type of produtc	Modified Alkyd
Colour	URKI-SYSTEM

#### SURFACE PREPARATION

-Iron and Steel: Degrease and deoxidize previously

-Wood: Brush and remove dust.

Recoatable with: URKI-RAPID, URKI-CLOR, URKI-FLEX, BESA-FER, BESA-LUX y URKI-SAL.

# **APPICATION INSTRUCTIONS**

Dipping: Dilute at 30-35 sec. Ford nº 4 with URKISOL-170



20-25 FORD nº 4



5-10 %



LIRKISOL 88 30-35 %





Tack free 45





5-10 %

# **FEATURES OF DRY FILM**

Theoretical yield (m²/l)	14 - 15 (35 my)
Gloss 60°-60°	Matt < 2 %
Second layer	1 h. ó 24 h.

# STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended. Can life: 2 years from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.