

F-350/2

2 K "LOW VOC" EPOXY PRIMER

Edition: 021 2016/02

Cod: 5035007360.00000.021

APPLICATION

Epoxy-Polyamide Primer formulated with anticorrosion pigments. Due to its high solid contents, 65 % in vol. more than 200 my can be achieved on each coat. Recommended for metallic structures, machinery, equipments and for processes demanding a high anticorrosion power. Also used as an alternative to conventional products in order to reduce VOC emissions in facilities and fulfill the European Directive 1993/13/CE.

It can also be applied as an intermediate coat in processes Zinc-Rich Epoxy Primer / Intermediate coat / PU Topcoat with high marine and industrial resistance.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,72 ± 0,03
Grinding Fineness (µ)	30 - 40
Supply viscosity at 20°C	110 - 130 KU
%Solids content (weigh / volume)	79 % ± 2 weight; 65 % ± 2 volume. (Mixture with hardener)
V.O.C. (g/l)	298 (Ready to use) Airless Application - (2004/42/CE) IIB (C) (540)
Type of product	Epoxy-Polyamide
Colour	70031 Grey

SURFACE PREPARATION

-Steel: Deoxidized and degreased manually. Previous blasting Sa 2,5 recommended.

-Galvanized: Previously degreased.

-Aluminium: Previously degreased. On fine surfaces sand previously.

Recoatable with Enamel URKI-POX, URKI-NATO, URKI-GLASS, BESA-GLASS, BESA-PUR, URKI-NATO/C, ALFAPUR 3748. In Low Voc systems recoatable with URKI-VOC or ALFAPUR 3790.

Do not paint if temperature is below 10°C and relative humidity above 75 %.

APPLICATION INSTRUCTIONS

With an Airless spray gun and 0,4-0,6 mm, nozzle 200 my. layers can be achieved, maximum dilution of 2 %.

Aerographical spray gun: 1,8-2,0 mm. nozzle

Brush application: only for small surfaces for touching up.

In order to improve drying time and hardening, use A-90002 accelerator (1-2 % of the mixture).



E-305
4:1 vol.



8 h



Spray Gun
35-45"



URKISOL-357
only for retouching



ø 1,8-2,0 mm
URKISOL 357
5-10 %



100-200 my



4-6 h. Tack free



ø 0,4-0,6 mm
URKISOL 357
2 %

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	4,5 (150 my)
Gloss 60°-60°	Matt-Satin
Second layer	4 - 6 h. (depending of thickness)



Bernardo Ecenarro S.A.

TECHNICAL DATA SHEET

BERNARDO ECENARRO, S.A.

Ugarte Industrialdea, 147

20720 Azkoitia (SPAIN)

Tel.: +34 +34 943 74 28 00

Fax: +34 +34 943 74 06 03

www.besa.es

F-350/2

2 K "LOW VOC" EPOXY PRIMER

Page 2 from 2

Edition: 021 2016/02

Cod: 5035007360.00000.021

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.
Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.