

URKI-TRAF

# **TECHNICAL DATA SHEET**

 BERNARDO ECENARRO, S.A.

 Ugarte Industrialdea, 147

 20720
 Azkoitia (SPAIN)

 Tel.: +34 943 74 28 00

 Fax: +34 943 74 06 03

 www.besa.es

Page 1 from 1

Edition: 021 2014/11

Cod: 6058500000.00000.021

# APPLICATION

# "USE ONLY IN INDUSTRIAL FACILITIES"

Synthetic paint, with excellent covering and rapid-drying qualities. This product has been developed for floor marking purposes in garages, industrial way networks, sports centres, etc.

## PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,60 ± 0,05
Grinding Fineness (µ)	40 - 50
Supply viscosity at 20°C	90 - 100 KU (Stormer)
%Solids content (weigth / volume)	72 % ± 2 weight; 50 % ± 2 volume.
V.O.C. (g/l)	496 (Ready to use)
Type of produtc	Synthetic Resin
Colour	Yellow 1442, White 9110

### SURFACE PREPARATION

Remove any dust and grease from the surface to be painted. Use Thinner nº. 10 for Cleaning.

#### APPICATION INSTRUCTIONS

Preferably apply with Airless. Dilution with 5-10 % URKISOL-170



#### FEATURES OF DRY FILM

Theoretical yield (m <sup>2</sup> /l)	10 - 12 (45 my)
Gloss 60°-60°	Matt <5%
Second layer	2 to 3 h.

#### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended. Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.