

VD 6635

2 K EPOXY TOPCOAT MATT

Edition: 020 2016/06

Cod: 6063500000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Top coat for glass. Conventional spraying.

High mechanical properties, hardness and elasticity .High chemical, G1 solution, and water resistance.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,00 - 1,50
Supply viscosity at 20°C	30 - 110 sec Ford nº4
%Solids content (weigth / volume)	45-65% weight
Type of product	Epoxy-Polyamide
Colour	Wide color range

SURFACE PREPARATION

The surface should be dry and free from dust, dirt grease and oil

It is recommended to flame the substrate.

Substrate temperature should no be higher than 40°C

APPLICATION INSTRUCTIONS

Conventional spray.

Mix well before use



E-8320
White 100:23 peso
Black 100:50 peso



8 h.



13-15"
FORD nº4



URKI-SOL 9041
30-50%



10-15 my



1-3'
20-25°C



15' / 150°C
10' / 180°C

FEATURES OF DRY FILM

Gloss 60°-60°	4 - 25 % (flat glass)
---------------	-----------------------

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended.

Can life: **1 year** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.