

URKI-RAPID SAT
 QUICK DRYING SATIN SYNTHETIC ENAMEL

URKI-SYSTEM
 CONVERTER:6002 / CONV U-RAPID SAT
 RELATION PASTE / CONV.: 25/75

Edition: 020 2011/11
 Cod: 6900200000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Suitable for agricultural machinery and public works, cranes, scaffolding, skips, etc.
 Nice satin finish and quick drying. Good resistance outdoors in solid colours.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,08 - 1,27
Grinding Fineness (µ)	20 - 30
Supply viscosity at 20°C	75 - 80 KU (Stormer)
%Solids content (weight / volume)	53 - 62 % weight; 42 - 45% volume.
V.O.C. (g/l)	594 (Ready to use)
Type of product	Modified Alkyd
Colour	URKI-SYSTEM

SURFACE PREPARATION

The surfaces to be painted, thoroughly degreased, should be primed with F-25 or F-29 Synthetic Primers
 If a higher rust protection is required, use the F-809 Zinc Phosphate Primer.

APPLICATION INSTRUCTIONS



25 ± 5"
 FORD nº 4



URKISOL 170
 30-35 %



30-40 my



Touch free 30'
 Tack free 2 h.

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	12 - 13 (35 my)
Gloss 60°-60°	30 - 40 %
Second layer	Before 2 hours or after 3 days

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.
 Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.