

BESA-VAL SAT
 QUICK DRYING SATIN INDUSTRIAL PAINT

URKI-SYSTEM
 CONVERTER: 6021 / CONV B-VAL SAT
 RELATION PASTE / CONV.: 25/75

Edition: 020 2011/11
 Cod: 6902100000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Suitable for agricultural machinery and for public works, cranes, lifts, construction material, etc, requiring quality at low cost. Outstands for its levelling and quick drying.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,15 - 1,35
Grinding Fineness (μ)	20 - 30
Supply viscosity at 20°C	70 - 80 KU (Stormer)
%Solids content (weight / volume)	57 - 65 % weight; 43 - 46% volume.
V.O.C. (g/l)	597 (Ready to use)
Type of product	Modified Alkyd
Colour	URKI-SYSTEM

SURFACE PREPARATION

The surface to be painted, thoroughly degreased, should be primed with F-463 or F-25, Synthetic Primers. If a higher rust protection is required, use the F-29 Zinc Phosphate, with a higher rust-protection.

APPLICATION INSTRUCTIONS



25 ± 5"
 FORD nº 4



URKISOL 170/300
 35-38 %



30-40 my



Touch free 30'
 Tack free 2 h.

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	12 - 13 (35 my)
Gloss 60°-60°	30 - 40 %
Second layer	48 h.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended. Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.