

**URKI-VAL**  
 QUICK-DRYING INDUSTRIAL PAINT

URKI-SYSTEM  
 CONVERTER: 6023 / CONV URKI-VAL  
 RELATION PASTE / CONV.: 12/88 VOL

Edition: 020 2012/05  
 Cod: 6902300000.00000.020

### APPLICATION

#### "USE ONLY IN INDUSTRIAL FACILITIES"

Suitable for the painting of agricultural machinery and public works, fork-lifts, cranes, construction material, in which applications low cost is required.

Outstands for its levelling, gloss and quick drying. It can be applied directly on steel for indoor jobs.

### PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,95 - 1,07
Grinding Fineness (μ)	5 - 10
Supply viscosity at 20°C	15 - 25 sec. Cup Ford nº 4
%Solids content (weight / volume)	35 - 45 % weight; 28 - 31 % volume.
V.O.C. (g/l)	605 (Ready to use)
Type of product	Modified Alkyd
Colour	URKI-SYSTEM

### SURFACE PREPARATION

Steel.

The surfaces should be thoroughly degreased and then primed with F-29 Zinc-Phosphate Primer, F-714 SHOP-PRIMER or F-862 Quick Drying Primer for a higher resistance.

### APPLICATION INSTRUCTIONS



20 ± 5"  
 FORD nº 4



Not diluted



30-40 my



Touch free 30'  
 Tack free 2 -3 h.

### FEATURES OF DRY FILM

Theoretical yield (m <sup>2</sup> /l)	8,0 - 9,0 (35 my)
Gloss 60°-60°	> 90 %
Second layer	24 h.

### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.