

URKI-SAL
 INDUSTRIAL PAINT

URKI-SYSTEM
 CONVERTER: 6036 / CONV U-SAL
 RELATION PASTE / CONV.: 15/85

Edition: 020 2011/11
 Cod: 6903600000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Synthetic Paint for the protection of metallic structures, boilermaking, agricultural equipment, etc.
 Presents a semigloss finish, level and quick drying with excellent adhesion.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,29 - 1,42
Grinding Fineness (μ)	25 - 35
Supply viscosity at 20°C	70 - 80 KU (Stormer)
%Solids content (weight / volume)	67 - 72 % weight; 50 - 53 % volume.
V.O.C. (g/l)	416

SURFACE PREPARATION

- Steel and Iron: Thoroughly degrease and deoxidize. Prime with F-25 or F-29 Synthetic Primers.
- Wood: Brush and remove any dust. Prime with Synthetic Sealant.

APPLICATION INSTRUCTIONS



20-25"
 Ford nº 4



URKISOL 222
 3-5 %



URKISOL 300
 25-30 %



30-40 my



Touch Free 1 h.
 Tack Free 4-5 h.

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	14 - 15 (35 my)
Gloss 60°-60°	50 - 70 %
Second layer	48 h. with Synthetics

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.
 Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.