

BESA-LUX
HIGH GLOSS SYNTHETIC ENAMEL

URKI-SYSTEM

CONVERTER: 6051 / CONV B-LUX

RELATION PASTE / CONV.: 35/65

Edition: 020 2011/11
Cod: 6905100000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Protection and decoration of metal or wooden surfaces, both indoors and outdoors.

Very easy to apply with a brush without sagging, easy levelling, high gloss and good resistance to all weather conditions.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,96 - 1,22
Grinding Fineness (μ)	5 - 10
Supply viscosity at 20°C	80 - 85 KU (Stormer)
%Solids content (weigh / volume)	59 - 70 % weight; 51 - 55 % volume.
V.O.C. (g/l)	398 (Ready to use) Brush application
Type of product	Alkyd
Colour	URKI-SYSTEM

SURFACE PREPARATION

-Iron or Steel: Thoroughly degrease and deoxidize Prime with F-29 or F-809 Anti-Rust Zinc Phosphate Primer.

-Wood: Prime with Synthetic Sealer and sand before applying the topcoat.

APPLICATION INSTRUCTIONS



20-25"
FORD nº 4



URKISOL 222



URKISOL 170
30-35 %



30-40 my



Touch free 1 h.
Tack free 8 h.

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	14 - 16 (35 my)
Gloss 60°-60°	> 90 %
Second layer	24 h.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.