

URKI-CEL
 SATIN PIGMENTED NITRO LACQUER

URKI-SYSTEM
 CONVERTER: 6350 / CONV U-CEL
 RELATION PASTE / CONV.: 25/75

Edition: 020 2011/11
 Cod: 693500000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Furniture lacquering, general wood decoration. It has pleasant Satin Matt Finish, excellent smoothing qualities and a rapid drying.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,95 - 1,15
Grinding Fineness (µ)	10 - 20
Supply viscosity at 20°C	85 - 90 KU (Stormer)
%Solids content (weight / volume)	32 - 43 % weight; 26 - 29 % volume.
V.O.C. (g/l)	663
Type of product	Nitro Synthetic
Colour	URKI-SYSTEM

SURFACE PREPARATION

Prime with Nitro Pore Covering Primer or even better with 2 K Polyurethane Pore Covering Primer., applying either 1 or 2 coats depending on surface condition, followed by careful sanding before lacquering.

APPLICATION INSTRUCTIONS

Apply 2 - 3 crossed coats wet on wet



20-25"
Ford nº 4



URKISOL 500
75-80 %



30-40 my



Touch Free 10'
Tack Free 30'

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	7 - 8 (35 my)
Gloss 60°-60°	30 - 40 %
Second layer	24 h.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.
 Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.