

URKI-CLOR
 ALKYD CHLORINATED RUBBER

URKI-SYSTEM
 CONVERTER: 6551 / CONV U-CLOR
 RELATION PASTE / CONV.: 25/75

Edition: 020 2011/11
 Cod: 6955100000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Widespread use on all types of machines, industrial vehicle, structures, cranes, industrial maintenance and in the protection of structures exposed to maritime influences or low chemical aggression.

Outstands for its resistance to humidity, mineral greases and oils, coolants, chemical products, etc. Quick-drying product.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,00 - 1,25
Grinding Fineness (μ)	5 - 10
Supply viscosity at 20°C	85 - 130" Ford Cup nº 4
%Solids content (weight / volume)	50 - 60 % weight; 40 - 44 % volume.
V.O.C. (g/l)	592 (Ready to use)
Type of product	Alkyd- Chlorinated Rubber
Colour	URKI-SYSTEM

SURFACE PREPARATION

The previously degreased surfaces should be primed first with F-809 or F-29 1K Zinc-Phosphate Primer.

APPLICATION INSTRUCTIONS

Brush: only for small surfaces.



20-25"
FORD nº 4



URKISOL 222
5 %



URKISOL 170
25-30 %



30-40 my



Touch Free 15-30'
Tack Free 1-1,5h.

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	11 - 12 (35 my)
Gloss 60°-60°	> 85 %
Second layer	Within 4 h. or wait 3-4 days

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.