

BESA-POL MAT
 MATT FINISH URETHANE LACQUER

URKI-SYSTEM
 CONVERTER: 6728 / CONV B-POL MAT
 RELATION PASTE / CONV.: 35/65

Edition: 021 2014/01
 Cod: 6972800000.00000.021

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Suitable for the protection and decoration of metal or wooden surfaces such as furniture, doors, windows, gates, etc. Outstands for its easy application by brush and levelling, which provides a pleasant finish, suitable for indoor decoration. Hard and elastic. Matt.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,00 - 1,25
Grinding Fineness (μ)	20 - 30
Supply viscosity at 20°C	80 - 95 KU (Stormer)
%Solids content (weight / volume)	55 - 65 % weight; 43 - 47 % volume.
V.O.C. (g/l)	491 (Ready to use) - Brush application
Type of product	Urethane Alkyd
Colour	URKI-SYSTEM

SURFACE PREPARATION

- Steel: Thoroughly degrease and deoxidize and apply one of two coats of Alfaglid 1005, F-29 or F-809 Zinc Phosphate Primers.
- Wood: Prime with Synthetic Sealers, and sand before recoating.

APPLICATION INSTRUCTIONS



20-25"
 FORD nº 4



URKISOL 222
 5-10 %



URKISOL 170
 25-30 %



30-40 my



Touch Free 1h.
 Tack Free 6 h.

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	12 - 13 (35 my)
Gloss 60°-60°	10 - 15 %
Second layer	24 h.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended. Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.