

URKI-POL
 2 K GLOSSY PIGMENTED POLYURETHANE LACQUER

URKI-SYSTEM
 CONVERTER: 6780 / CONV U-POL
 RELATION PASTE / CONV.: 35/65

Edition: 020 2011/11
 Cod: 697800000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Lacquering of furniture, decoration of wood in general.

Outstands for its body and filling capacity, hardness, elasticity and resistance to domestic products. Very high gloss. It does not yellow.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,05 -1,30
Grinding Fineness (μ)	5 - 10
Supply viscosity at 20°C	80 - 100 sec. Ford nº 4
%Solids content (weight / volume)	45 - 54 % weight; 37 - 40 % volume. (Mixture with hardener)
V.O.C. (g/l)	540 (Mixture with hardener)
Type of product	Polyester-Polyurethane
Colour	URKI-SYSTEM

SURFACE PREPARATION

Prime wood with 2 K Pore Covering Polyurethane Primers. applying 1 or 2 coats depending on condition of the surface, followed by a careful sanding before lacquering with URKI-POL.

APPLICATION INSTRUCTIONS

Leave the paint settle 15´ before painting.



E-141
1:1 vol.



2-3 h.



20"
FORD nº 4



URKISOL 900/P
2-3 %



35-45 my



Touch Free 30´
Tack Free 1 h.

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	9 - 10 (40 my)
Gloss 60°-60°	90 - 95 %
Second layer	18 h.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.