

### URKI-POL SAT

2 K SATIN PIGMENTED POLYURETHANE LACQUER

### URKI-SYSTEM

CONVERTER: 6781 / CONV U-POL SAT

RELATION PASTE / CONV.: 35/65

Edition: 020 2011/11

Cod: 6978100000.00000.020

### APPLICATION

#### "USE ONLY IN INDUSTRIAL FACILITIES"

Lacquering of furniture, decoration of wood in general.

Outstands for its filling and smoothing power, scratch proof, hardness and elasticity.

Pleasant satin finish, resistant to domestic products. It does not yellow.

### PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,10 - 1,40
Grinding Fineness (μ)	20 - 25
Supply viscosity at 20°C	100 - 120 sec. Ford nº 4
%Solids content (weight / volume)	48 - 55 % weight; 37 - 40 % volume. (Mixture with hardener)
V.O.C. (g/l)	546 (Mixture with hardener)
Type of product	Polyester-Polyurethane
Colour	URKI-SYSTEM

### SURFACE PREPARATION

Primer wood with 2 K. Polyurethane Pore Covering Primer, applying 1 or 2 coats depending on the condition of the surface, followed by a fine sanding before lacquering with URKI-POL SAT.

### APPLICATION INSTRUCTIONS

Leave the paint settle 15´ before painting.



E-140  
2:1 vol.



2-3 h.



20"  
FORD nº 4



URKISOL 900/P  
25-30 %



30-40 my



Touch Free 30´  
Tack Free 1 h.

### FEATURES OF DRY FILM

Theoretical yield (m²/l)	9 - 10 (40 my)
Gloss 60º-60º	30 - 40 %
Second layer	12 h.

### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.