

**ALFA-PUR 3795**

UHS SINGLE COAT ANTICORROSION PUR 2 K

**URKI-SYSTEM**

CONVERTER: 6795/ CONV A-PUR 3795  
RELATION PASTE / CONV.: 35/65 weight (25/75 vol.)

Edition: 023 2017/05

Cod: 6979500000.00000.023

**APPLICATION**

High Solids Single Coat anticorrosion Enamel.

Indicated for the painting of machinery and industrial vehicle with Air-mix or Air-less Equipment.

Elasticity, body, gloss and outdoor resistance.

Salt Spray Test: 350 h.

ALFA-PUR 3795 meets the requirements for category C3 MEDIUM in accordance to ISO 12944-2 certified by an independent approved Laboratory (Shotblasted Steel Sa 2,5).

**PHYSICAL PROPERTIES**

Density at 20°C (g/cc)	1,16 - 1,42
Grinding Fineness (µ)	10 - 20
Supply viscosity at 20°C	70 - 75 KU
%Solids content (weigh / volume)	59 - 67 % weight; 47 - 50 % volume. (Mixture with hardener)
V.O.C. (g/l)	420 (2004/42/CE) IIB (D) (420)
Type of product	Polyester-Polyurethane
Colour	URKI-SYSTEM

**SURFACE PREPARATION**

-Steel: The surfaces to be painted, thoroughly degreased.

For a higher rust protection, Sa 2,5 shotblating required.

**APPLICATION INSTRUCTIONS**

Leave the paint settle 15´ before painting.



E-135  
4:1 weight  
3:1 Vol



> 2 h.



45-55" Air-less  
25-30" Spray-gun  
Ford nº 4



URKISOL 8229/3700  
25-30%  
Ø 1.4-1.6 mm



80-100 my



4-5 h. Tack Free



15-30´  
70°C/30´  
(In cabin)



URKISOL 8229/3700  
3-7 %  
0.013-0.015"



URKISOL 8229/3700  
3-7 %  
0.013-0.015"

**FEATURES OF DRY FILM**

Theoretical yield (m <sup>2</sup> /l)	6 - 7 (80 my)
Gloss 60°-60°	> 85 %
Second layer	3 h. after spray-booth drying

**STORAGE**

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.



Bernardo Ecenarro S.A.

## TECHNICAL DATA SHEET

**BERNARDO ECENARRO, S.A.**

Ugarte Industrialdea, 147  
20720 Azkoitia (SPAIN)  
Tel.: +34 +34 943 74 28 00  
Fax: +34 +34 943 74 06 03  
www.besa.es

Page 2 from 2

**ALFA-PUR 3795**

UHS SINGLE COAT ANTICORROSION PUR 2 K

URKI-SYSTEM

CONVERTER: 6795/ CONV A-PUR 3795  
RELATION PASTE / CONV.: 35/65 weight (25/75 vol.)

Edition: 023 2017/05

Cod: 6979500000.00000.023