

**VD 7020**  
MATT EPOXY CLEARCOAT

Edition: 020 2016/06  
Cod: 7002000000.00000.020

### APPLICATION

**"USE ONLY IN INDUSTRIAL FACILITIES"**

Top coat for glass. Conventional spraying.

High mechanical properties, hardness and elasticity .High chemical, G1 solution, and water resistance.

### PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,03 ± 0,02
Supply viscosity at 20°C	26 ± 5 sec. Ford n°4
%Solids content (weigh / volume)	44 % ± 2 weight
Type of product	Epoxy-Polyamide
Colour	Transparent

### SURFACE PREPARATION

The surface should be dry and free from dust, dirt, grease and oil.

It is recommended to flame the substrate.

Substrate temperature should no be higher than 40°C.

### APPLICATION INSTRUCTIONS

Conventional spraying.

Mix well before use.



E-8320  
100:40 weight



8 h.



13-15"  
FORD n°4



URKI-SOL 9041  
30-50%



10-15 my



1-3'  
20-25°C



15' / 150°C  
10' / 180°C

### FEATURES OF DRY FILM

Gloss 60°-60°	8 ± 1 (flat glass)
---------------	--------------------

### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended.

Can life: **1 year** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.