

TECHNICAL DATA SHEET

BERNARDO ECENARRO, S.A.

Ugarte Industrialdea, 147
20720 Azkoitia (SPAIN)
Tel.: +34 +34 943 74 28 00
Fax: +34 +34 943 74 06 03

www.besa.es

Page 1 from 1

Edition: 020 2016/06 Cod: 7005100000.00000.020

VD 7051

PUR SOFT MATT CLEARCOAT

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Soft touch two-component clear coat. Conventional spraying. Good mechanical properties, scratch resistance and elasticity.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,00 ± 0,02
Supply viscosity at 20°C	35 - 40 sec Ford nº4
%Solids content (weigth / volume)	47 % ± 2 weight
Type of produtc	Polyurethane
Colour	Transparent matt

SURFACE PREPARATION

On glass substrates it must be applied first a flash primer like VD 3100 or VD 3105. The surface should be dry and free from dust, dirt, grease and oil.

APPLICATION INSTRUCTIONS

Conventional spraying.



VD8287 100:10 weight



It is recommended to use a two component spraying system



28-33" FORD nº4



VD 9041 5-10%



20-50 m



20-25°C



15' / 150°C 10' / 180°C Glass



Plastic

FEATURES OF DRY FILM

Gloss 60°-60°	10 % ±0.5 (flat glass)
0.000 00	120 70 = 010 (11de glado)

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended. Can life: **1 year** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.