

PD 7080 2K CHROME FINISH CLEARCOAT

## **TECHNICAL DATA SHEET**

BERNARDO ECENARRO, S.A. Ugarte Industrialdea, 147 20720 Azkoitia (SPAIN) Tel.: +34 +34 943 74 28 00 Fax: +34 +34 943 74 06 03 www.besa.es

Page 1 from 1

Edition: 020 2016/06 Cod: 700800000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

2K clearcoat with high gloss for chrome finishes

### PHYSICAL PROPERTIES

| Density at 20ºC (g/cc)            | 0,93 - 0,98                       |  |
|-----------------------------------|-----------------------------------|--|
| Supply viscosity at 20°C          | 16 - 20 sec Ford nº 4             |  |
| %Solids content (weigth / volume) | 32 % ± 2 weight; 24 % ± 2 volume. |  |
| Type of produtc                   | Polyacrilate                      |  |
| Colour                            | Colorless                         |  |

#### **APPLICATION INSTRUCTIONS**











10



100:11 weight

# FEATURES OF DRY FILM

| Gloss 60°-60°   | >90 |  |
|-----------------|-----|--|
| 01033 00 - 00 - | 290 |  |

#### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended. Can life: 12 months from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.