

TECHNICAL DATA SHEET

BERNARDO ECENARRO, S.A.

Ugarte Industrialdea, 147 20720 Azkoitia (SPAIN) Tel.: +34 +34 943 74 28 00 Fax: +34 +34 943 74 06 03

www.besa.es

Page 1 from 1

Edition: 021 2017/07

Cod: 7050605122.00000.021

F-3131 STRIPPING LACQUER

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Stripping Lacquer for temporary protection, providing the product a good anti-rust qualities for not excessively long periods of time and easy to peel off in one single strip.

Very useful in Aluminium Carpentry, protection of Steel parts during storage and transport, protection of mechanized areas in the Machine Tool sector, etc.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0.91 ± 0.02
Grinding Fineness (μ)	5 - 10
Supply viscosity at 20°C	120" ± 10 Ford nº 4
%Solids content (weigth / volume)	$30\% \pm 2$ weight; $21\% \pm 2$ volume.
V.O.C. (g/l)	645
Type of produtc	Vinyl
Colour	Blue 5122

SURFACE PREPARATION

 $\label{eq:continuous} \mbox{ Direct application on the metallic surface, Steel or Aluminium thoroughly degreased.}$

Avoid the application of this product on surfaces subject to temperatures of above 70-80°C or on surfaces painted with products of a low reticulation.

APPICATION INSTRUCTIONS

Application by brush recommend in order to achieve a thickner film and therefore easier to strip off.



15-18" FORD nº 4



Viscosity



Thinner URKISOL 300 90-100 %



20-40 my



Tack Free 60

FEATURES OF DRY FILM

Theoretical yield (m²/l)	7 - 8 (30 my)
Gloss 60°-60°	Satin
Second layer	

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended. Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.